

~~CONFIDENTIAL~~

EXPLOITATION REPORT

FRAGMENT, METAL, RECOVERED IN THE REPUBLIC OF THE CONGO,
ORIGIN BELIEVED TO BE AN UNIDENTIFIED FLYING OBJECT
(COUNTRY UNIDENTIFIED) (U)
MXN-25500

SECTION I. (C) Purpose (U)

1. (C) The purpose of this report is to present the results of the exploitation of a metallic fragment recovered near the town of Kerehena in the Republic of the Congo. The recovery was the result of a ground-level search which was conducted after an unidentified flying object exploded and fell to earth in the area. The sighting and recovery took place sometime between 10 and 15 October 1965. Other than a reported east-to-west direction of flight for the UFO, specific observation and recovery details are lacking.

SECTION II. (C) Description (U)

2. (C) Details concerning the exact location and characteristics of impact are unknown. However, the appearance of the fragment indicated exposure to high temperatures prior to impact (burn). Impact of the specimen had little or no effect on its final condition or appearance. The fragment weighed 0.41g, had an indefinite density of approximately iron and measured 2.25 x 1.75 x 1.0 inches. The top and side views of the specimen were rounded and appeared to have been shaped by heating and melting. This is illustrated in Figures 1 and 2. The V-shaped groove, visible in Figure 1, is the outline of an insert of steel that differs materially from the rest of the specimen. Figure 3 shows the side view of the end shown in Figure 1.

GROUP 1
EXCLUDED FROM AUTOMATIC
DOWNGRADING AND
DECLASSIFICATION

~~CONFIDENTIAL~~

REGRADED UNCLASSIFIED

ON 18 FEB 1992

BY CDR USAN/SGM EOT/RO

AUTH Para 1-603 DOD 5200.10

POOR ORIGINAL

~~CONFIDENTIAL~~

and was composed of six machined or formed V-shaped fins extending along the major axis of the fragment.

SECTION III. (C) Conclusion.

3. (C) The fragment was originally part of an electrical component and could be identified as a motor, generator armature, or associated electrical regulator or control device.

4. (C) The fragment was constructed of .10-inch thick silicon steel laminate stacked on a central mild steel core or shaft.

5. (C) Materials, processes, dimensions, etc., as such, prevent determination of exact origin (country).

6. (C) Surface appearance and microstructure of the specimen indicates exposure to temperatures in excess of 2500° F.

SECTION IV. (C) Explanation. Para (C)

7. (C) The recovered specimen was .41 grams and had a density closely approximating that of steel. The specimen had a heavy oxide scale on its surface, which is characteristic of temperatures in excess of 2500° F. While there are no indications of impact, the deformed metal, as shown in Figures 4 and 7, would substantiate the conclusion that the item was moving at a high velocity when it was shot.

8. (C) Fabrication of the item was accomplished utilizing more or less standard procedures for fabricating electric motor armatures.

Armature laminates were stamped (punched) from approximately .012-inch sheet steel, copper-plated, and assembled on a mild steel shaft approximately .435 inches in diameter. Following assembly, the laminates were joined by soldering or diffusion-bonding of the copper.

REGRADED UNCLASSIFIED
ON 10 FEB 1999
BY CDR USAINSCOM F017PO
ADJ1: Para 1-603 DOD 5200.1R

~~CONFIDENTIAL~~

CONFIDENTIAL

CONFIDENTIAL

placing. This can be accomplished by tightly compacting the laminate assembly and heating in a furnace. Temperature required for bonding of the copper depends upon the degree compact on or pressure; the higher pressures requiring proportionately lower temperatures.

9. (C) A cross-section (transverse to the length of the specimen) is shown in Figure 5. The light-colored, thin lines are the edges of individual laminates, caused by cutting at an angle to, instead of parallel to, the laminates. These thin lines or petals are "T" shaped. This shape is used to help the binding wire in place and is found on high RPM motors. The melted condition of some of the "T's" is indicative of the high heating conditions experienced. The outer surface of the armature shaft is serrated to prevent axial slippage of the laminates.

10. (C) The lamination or sticking of individual laminates is clearly illustrated in Figure 6. The space between laminates on the fin at the top of the photograph is due to the melting and flowing of the copper plating during the high temperature exposure of the specimen. Some of the copper has been removed from the fin at the bottom of the photograph. A rearward cross-section of this area is shown in Figures 7 and 8.

11. (C) Another result of intense heating was the gradual strain along the steel laminates. The laminates were made of steel and the lamination along in Figures 9 and 10 illustrates strain along the steel laminates. The laminates are made of steel and are comparable to laminates 2 of the motor.

REGRADED UNCLASSIFIED
ON 10 FEB 1992
BY CBR/USAINSCOM/F01/P6
AUTH Para 1-603 DOD 5200.1-R

~~CONFIDENTIAL~~

intense heat and then cooled at a comparatively slow rate.

12. (C) The light material between the laminations in Figure 9 is plated copper that melted and flowed between the laminations when the entire specimen was hot. A photomicrograph of this is shown in Figure 11.

13. (C) Analysis of the steel discloses the following:

<u>Element</u>	<u>Percent Present (Weight)</u>
Carbon	
Manganese	
Silicon	
Nickel	less than 0.10
Chromium	0.37
Molybdenum	less than 0.01

14. (C) Chemical composition of the steel laminations was as follows:

<u>Element</u>	<u>Percent Present (Weight)</u>
Manganese	0.25
Silicon	(0.5)
Nickel	less than 0.10
Chromium	
Molybdenum	less than 0.01

REGRADED UNCLASSIFIED
ON 10 FEB 1992
BY CDR USAINSCOM F01/PO
AUTH Para 1-603 DOD 5200.1R

~~CONFIDENTIAL~~




Figure 1: Top View of [unclear] 265-61




Figure 2: Side View of [unclear]

DO NOT REPRODUCE ORIGINAL

UNCLASSIFIED




Figure 3 (Opposite View of Fig. 2 (a))



Figure 4 (Opposite View of Fig. 2 (b))

UNCLASSIFIED

UNCLASSIFIED





Figure 3. Cross-section of the structure shown in Figure 1. The structure is a cross-section of a structure, possibly a component of a machine or a biological structure. The diagram shows various layers and components, with dimensions and labels indicating specific parts.



TOP SECRET

UNCLASSIFIED



Figure 7. Micrograph Cross Section of
Leaded Area
Magnification: 75X (40)





Figure 8. Micrograph Cross Section of
Leaded Area
Magnification: 75X (40)

UNCLASSIFIED

Figure 9 (Micrograph)
Laminar Structure
Magnification 63
(In Nitral Etchant)

FOR ORIGINAL



UNITED STATES DEPARTMENT OF THE ARMY
OFFICE OF THE ADJUTANT GENERAL
WASHINGTON, D.C. 20315

ORIGINAL